



**三环集团**  
— SINCE 1970 —

**潮州三环（集团）股份有限公司**

CHAOZHOU THREE-CIRCLE(GROUP)CO.,LTD

地址：中国广东省潮州市凤塘三环工业城 邮编（Post Code）：515646

ADD:Sanhuan Industrial District,Fengtang Chaozhou,Guangdong,China

# 承 认 书

## SPECIFICATION FOR APPROVAL

客户名称：  
CUSTOMER: \_\_\_\_\_

产品名称 多层片式瓷介电容器  
PARTNAME: \_\_\_\_\_

产品规格 M3L 系列

SPECIFICATION: \_\_\_\_\_

承认书编号

APPROVAL SHEET NO.: \_\_\_\_\_ DRAAW101J/0

发出日期

ISSUED DATE: \_\_\_\_\_

制造 MANUFACTURER			客户 CUSTOMER		
批准 APPROVED	审核 CHECKED	经办 PREPARED	批准 APPROVED	审核 CHECKED	经办 PREPARED
孙鹏	王彬彬	陈家锐			

文件编号	DRAAW101J/0		页数	28
文件名称	多层片式陶瓷电容器(产品承认书)		制订日期	2012.01
版数	制定、修订日期	页数	制定、修订内容	登记者
E/0	2012-2-29	25	制定节能灯专用产品承认书	张国信
F/0	2014-05-05	26	换版	张国信
G/0	2017-07-01	26	换版	张国信
H/0	2020-03-16	26	换版	张国信
I/0	2022-7-12	25	换版	陈家锐
I/1	2022-11-28	27	增加 RoHS、REACH 和无卤要求	陈家锐
I/2	2023-8-5	28	修改尺寸公差，绝缘电阻，稳态湿热技术要求	陈家锐
I/3	2023-9-25	28	更新容值，修改深圳基地地址和中盒包装尺寸	陈家锐
J/0	2024-3-14	28	新增 M3L 工作温度	陈家锐

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

## 目录

1. 电容器及介质分类.....	3
2. 产品命名.....	4
3. 产品容量范围 .....	5
4. 产品尺寸.....	6
5. 技术要求和测试条件.....	7
6. 产品包装.....	17
7. MLCC 使用注意事项.....	22

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

## 1. 电容器及介质分类 Types of Capacitor and Dielectric Material


※M3L：此类介质材料的电容器为 I 类电容器，此类产品电性能较稳定，几乎不随电压和时间变化，容量随温度变化率为 0.1%/℃，适用于损耗低、要求较高的电路中。

※M3L : The capacitor of this kind dielectric material is considered as Class I capacitor. The electrical properties of M3L capacitor are stably and have little change with voltage and time. The coefficient of temperature is 0.1%/℃, They are suited for applications where low-losses and high-stability are required.

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

## 2. 产品命名 Product Parts Numbering System

(例) (example)



材质 Dielectrics	工作温度范围 Operating Temperature Range	温度系数或温度特性 Temperature Characteristic
M3L	-55°C~+125°C	-1000±500ppm/°C

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

### 3. 产品容量范围 Product Capacitance Range

尺寸	材质	M3L	
	厚度	电压 (V)	容量范围
0603	C	50	471~103
0805	D	50	102~223
	F	50	102~333
	D	500	471~102
	F	500	102~152
1206	F	50	153~104
	H	25	104~124
	H	100	103~104
	D	630	102~332
	F	630	332~472
	H	630	472~103

以上容量仅供参考，具体容量取决于使用要求。


Above capacitance for reference only, actual capacitance range depends on the use requirement.

产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No.
	DRAAW101J/0

#### 4. 产品尺寸 Dimensions

规格：0603、0805、1206。

Chip Size：0603、0805 and 1206。



规格 Type	L	W	e	g min	T (mm) / 代码 Code		
	(mm)	(mm)	(mm)	(mm)			
0603	1.60±0.10	0.80±0.10	0.2~0.6	0.5	0.80±0.10	C	
0603	1.60±0.20	0.80±0.20	0.2~0.6	0.5	0.80±0.20	C	*1
0603	1.60-0/+0.3	0.80-0/+0.3	0.2~0.6	0.5	0.80-0/+0.3	C	*2
0805	2.00±0.10	1.25±0.10	0.2~0.7	0.7	0.60±0.10	B	
					0.85±0.10	D	
					1.25±0.10	F	
0805	2.00±0.20	1.25±0.20	0.2~0.7	0.7	0.60±0.10	B	*1
					0.85±0.20	D	
					1.25±0.20	F	
0805	2.00-0/+0.3	1.25-0/+0.3	0.2~0.7	0.7	1.25-0/+0.3	F	*2
1206	3.20±0.20	1.60±0.20	0.3~0.8	1.6	0.85±0.10	D	
					1.00±0.10	E	
					1.25±0.20	F	
					1.60±0.20	H	
1206	3.20±0.30	1.60±0.30	0.3~0.8	1.6	0.85±0.10	D	*1
					1.00±0.10	E	
					1.25±0.20	F	
					1.60±0.30	H	

\*1 标识该规格型号标识为 1uF 及以上规格产品尺寸。

\*1 Identification: The model identification of this type is 1uF and above specifications of product size.

\*2 标识该规格型号标识为 4.7uF 及以上规格产品尺寸。

\*2 Identification: The model identification of this type is 4.7uF and above specifications of product size.

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

## 5. 技术要求和测试条件 Specification and Test Condition

### 5.1 外观 Appearance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	无损伤或异常 No defects or abnormalities	目视检查 Visual inspection.

### 5.2 尺寸 Dimensions

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	在要求的范围内 Within the specified dimensions	用千分尺 Using calipers on micrometer

### 5.3 容量 Capacitance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	在要求的容值容差范围内 Within the specified tolerance J: ±5%; K: ±10%; M: ±20%	1.0±0.2Vrms, 1KHz±10% 20~30℃, 环境湿度≤70%预处理后 48hrs。 at 20~30℃, humidity under 70%, 48hrs after annealing

### 5.4 损耗 Dissipation Factor

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	DF≤2.5%	1.0±0.2Vrms, 1KHz±10% (Cp>10uF, 0.5±0.2Vrms, 120Hz) 20~30℃, 环境湿度≤70%预处理后 48hrs。



产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

### 5.5 绝缘电阻 Insulation Resistance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition												
M3L	$U_R \leq 50V$ , 大于 $10 G\Omega$ 或 $100\Omega \cdot F / CR$ (大于其中较小的数值) $U_R > 50V$ , 大于 $4G\Omega$ 或 $100\Omega \cdot F / CR$ (大于其中较小的数值) $U_R \leq 50V$ , More than $10 G\Omega$ or $100\Omega \cdot F / CR$ , whichever is smaller. $U_R > 50V$ , More than $4 G\Omega$ or $100\Omega \cdot F / CR$ , whichever is smaller.	$20 \sim 30^\circ C$ , 环境湿度小于 70%, 测量时间 $60 \pm 5$ 秒, 测量电压如下: <table border="1" style="margin: 5px 0;"> <tr> <td>额定电压</td> <td><math>\leq 400V</math></td> <td><math>&gt; 400V</math></td> </tr> <tr> <td>测量电压</td> <td><math>U_R</math></td> <td>400V</td> </tr> </table> Test for $60 \pm 5$ sec, at $20 \sim 30^\circ C$ , humidity under 70%, under test voltage: <table border="1" style="margin: 5px 0;"> <tr> <td><math>U_R</math></td> <td><math>\leq 400V</math></td> <td><math>&gt; 400V</math></td> </tr> <tr> <td><math>U_T</math></td> <td><math>U_R</math></td> <td>400V</td> </tr> </table>	额定电压	$\leq 400V$	$> 400V$	测量电压	$U_R$	400V	$U_R$	$\leq 400V$	$> 400V$	$U_T$	$U_R$	400V
额定电压	$\leq 400V$	$> 400V$												
测量电压	$U_R$	400V												
$U_R$	$\leq 400V$	$> 400V$												
$U_T$	$U_R$	400V												

### 5.6 耐电压 Dielectric Strength

类型 Dielectrics	额定电压范围 Rated voltage range	耐电压性能测试方法 Measuring Method														
M3L	无损坏或异常 No defects or abnormalities.	当在电容器的两端施加试验电压 5 秒钟, 充放电电流不超过 50 mA <table border="1" style="margin: 5px 0;"> <tr> <th>额定电压</th> <th>测试电压</th> </tr> <tr> <td>25V</td> <td>62.5V</td> </tr> <tr> <td>50V</td> <td>125V</td> </tr> <tr> <td>100V</td> <td>200V</td> </tr> <tr> <td>400V</td> <td>750V</td> </tr> <tr> <td>500V</td> <td>800V</td> </tr> <tr> <td>630V</td> <td>900V</td> </tr> </table> Failure shall be observed the testing voltage is applied between the terminations for 5 seconds, provided the charge /discharge current is less than 50mA	额定电压	测试电压	25V	62.5V	50V	125V	100V	200V	400V	750V	500V	800V	630V	900V
额定电压	测试电压															
25V	62.5V															
50V	125V															
100V	200V															
400V	750V															
500V	800V															
630V	900V															


产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No. DRAAW101J/0
-------------------------------------	--------------------------------

**5.7 静电容量温度特性 Temperature Coefficient of Capacitance**

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition														
M3L	容量变化在 $-0.1\%/^{\circ}\text{C} \sim -0.2\%/^{\circ}\text{C}$ 以内 Temperature coefficient within $-0.1\%/^{\circ}\text{C} \sim -0.2\%/^{\circ}\text{C}$	<p>按系列温度顺序测试电容容量 Measure capacitance under follow table list temperature:</p> <table border="1" style="margin-left: 20px;"> <thead> <tr> <th colspan="2" style="text-align: center;">步骤</th> </tr> <tr> <th colspan="2" style="text-align: center;">STEP</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">1</td> <td style="text-align: center;"><math>25 \pm 2</math></td> </tr> <tr> <td style="text-align: center;">2</td> <td style="text-align: center;"><math>-55 \pm 3</math></td> </tr> <tr> <td style="text-align: center;">3</td> <td style="text-align: center;"><math>25 \pm 2</math></td> </tr> <tr> <td style="text-align: center;">4</td> <td style="text-align: center;"><math>125 \pm 3</math></td> </tr> <tr> <td style="text-align: center;">5</td> <td style="text-align: center;"><math>25 \pm 2</math></td> </tr> </tbody> </table> <p>1) M3L</p> <p>温度系数的计算以第 3 步骤测量电容容量为参考 The capacitance drift is calculated by dividing the differences between the maximum and minimum measured values in the step 1,3 and 5.</p>	步骤		STEP		1	$25 \pm 2$	2	$-55 \pm 3$	3	$25 \pm 2$	4	$125 \pm 3$	5	$25 \pm 2$
步骤																
STEP																
1	$25 \pm 2$															
2	$-55 \pm 3$															
3	$25 \pm 2$															
4	$125 \pm 3$															
5	$25 \pm 2$															

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

### 5.8 附着力 Adhesion

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	端电极无松动, 也无其它不良现象 No removal of the terminations or other defect shall occur.	施加 6N(=600g*f)的压力, 并保持 10±1 秒 The pressurizing force shall be 6N (=600g*f) and the duration of application shall be 10±1sec. 

### 5.9 可焊性 Solderability of Termination


类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	端电极挂锡面积不小于 95%，针孔或粗糙面积小于 5% 95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots.	锡炉温度：245±5℃ 浸入时间：2±1 秒 两侧端电极完全浸入焊锡炉 Solder temperature: 245±5℃ Dipping time: 2±1 seconds. Completely soak both terminal electrodes in solder

### 5.10 耐焊性 Resistance to leaching

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	端电极挂锡面积不小于 95%，针孔或粗糙面积小于 5%，外观无开裂 95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots. No remarkable visual damage.	预热：120℃~150℃/60 秒 锡炉温度：270±5℃ 浸入时间：10±1 秒 两侧端电极完全浸入焊锡炉 Solder temperature: 270±5℃ preheated: 120℃~150℃/60sec Dipping time: 10±1 seconds. Completely soak both terminal electrodes in solder

<p>产品标准书 SPECIFICATION FOR APPROVAL</p>	<p>编号 Document No. DRAAW101J/0</p>
---	--

### 5.11 端电极结合强度 Bending

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
<p>M3L</p>	<p>无可见损伤; 容量变化小于等于±5% 或 0.5 PF No remarkable visual damage Cp change ≤ ±5% ,or ≤ 0.5 pF</p>	<p>将片状电容器安装在测试夹具上，按图所示方向以 1.0mm/s 的速率施加压力，弯曲 1mm。 Solder the capacitor on testing substrate and put it on testing stand. The middle part of substrate shall successively be pressurized by pressuring rod at a rated of about 1.0mm/sec. Until the deflection become means of the 1.0mm.</p> 

产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No. DRAAW101J/0
-------------------------------------	--------------------------------

### 5.12 耐焊接热 Resistance to Soldering Heat

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	无明显可见损伤 容量变化: $-2.5\% \leq \Delta C/C \leq +2.5\%$ 或 $-0.25\text{pF} \leq \Delta C/C \leq +0.25\text{pF}$ (取较大值) 以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within $\pm 2.5\%$ or $\pm 0.25\text{pF}$ , whichever is larger. DF meets initial standard value. IR meets initial standard value.	焊接温度: $270 \pm 5^\circ\text{C}$ 预热: $120 \sim 150^\circ\text{C}$ 60 秒 浸入时间: $10 \pm 1$ 秒 在室温下放置 $24 \pm 2$ (M3L) 小时以后测量 试验后在标准条件下恢复 测量初始值 Soldering temperature: $270 \pm 5^\circ\text{C}$ Preheating: $120 \sim 150^\circ\text{C}$ 60sec. Dipping time: $10 \pm 1$ seconds. Measurement to be made after being kept at room temperature for $24 \pm 2$ (M3L) hours. Recovery for the following period under the standard condition after test. Perform the initial measurement.

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

### 5.13 温度快速循环 Temperature Cycle

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition															
M3L	<p>无明显可见损伤 容量变化在 <math>-2.5\% \leq \Delta C/C \leq 2.5\%</math> 或 <math>-0.25\text{pF} \leq \Delta C \leq 0.25\text{pF}</math>（取较大值）以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within <math>\pm 2.5\%</math> or <math>\pm 0.25\text{pF}</math>, whichever is larger. DF meets initial standard value. IR meets initial standard value</p>	<p>按下列步骤进行 5 次循环： To perform 5 cycles of the stated environment</p> <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th style="text-align: center;">步骤 Step</th> <th style="text-align: center;">温度 Temperature</th> <th style="text-align: center;">时间 Time</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">1</td> <td style="text-align: center;">下限类别温度 <math>+0/-3^{\circ}\text{C}</math> Min. operating Temp. <math>+0/-3^{\circ}\text{C}</math></td> <td style="text-align: center;">30min</td> </tr> <tr> <td style="text-align: center;">2</td> <td style="text-align: center;"><math>25^{\circ}\text{C}</math></td> <td style="text-align: center;">2~3 min</td> </tr> <tr> <td style="text-align: center;">3</td> <td style="text-align: center;">上限类别温度 <math>+3/-0^{\circ}\text{C}</math> Max. operating Temp. <math>+3/-0^{\circ}\text{C}</math></td> <td style="text-align: center;">30 min</td> </tr> <tr> <td style="text-align: center;">4</td> <td style="text-align: center;"><math>25^{\circ}\text{C}</math></td> <td style="text-align: center;">2~3 min</td> </tr> </tbody> </table> <p>在室温下放置 <math>24 \pm 2</math> (M3L) 小时以后测量</p> <p>测量初始值 Measurement to be made after being kept at room temperature for <math>24 \pm 2</math> hrs (M3L) at room temperature, then measure. Perform the initial measurement.</p>	步骤 Step	温度 Temperature	时间 Time	1	下限类别温度 $+0/-3^{\circ}\text{C}$ Min. operating Temp. $+0/-3^{\circ}\text{C}$	30min	2	$25^{\circ}\text{C}$	2~3 min	3	上限类别温度 $+3/-0^{\circ}\text{C}$ Max. operating Temp. $+3/-0^{\circ}\text{C}$	30 min	4	$25^{\circ}\text{C}$	2~3 min
步骤 Step	温度 Temperature	时间 Time															
1	下限类别温度 $+0/-3^{\circ}\text{C}$ Min. operating Temp. $+0/-3^{\circ}\text{C}$	30min															
2	$25^{\circ}\text{C}$	2~3 min															
3	上限类别温度 $+3/-0^{\circ}\text{C}$ Max. operating Temp. $+3/-0^{\circ}\text{C}$	30 min															
4	$25^{\circ}\text{C}$	2~3 min															

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

**5.14 稳态湿热 Moisture Resistance ,steady state**

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	外观无明显可见损伤 容量变化在±5%或 ±0.5pF（取较大值）以内 DF 为初始值的 2 倍以下 IR: 大于等于 1000MΩ或 10Ω·F(取较小值) No remarkable visual damage Cp change within ±5% or ±0.5pF, whichever is larger. DF:Not more than 2 times of initial value R*C≥1000MΩ or 10Ω·F, whichever is smaller	测试温度: 40±2℃ 湿度: 90~95% RH 测试时间: 500 ±12hrs 在室温下放置 24±2 (M3L)小时以后测量 测量初始值 Test temperature: 40±2℃ Humidity: 90~95% RH Testing time: 500 ±12hrs Measurement to be made after being kept at room temperature for 24±2hrs (M3L) Perform the initial measurement.

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

### 5.15 耐湿负荷 Damp heat with load

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	<p>外观无明显可见损伤</p> <p>容量变化在<math>\pm 7.5\%</math>或<math>\pm 0.75\text{pF}</math>（取较大值）以内</p> <p>DF 为初始值的 2 倍以下</p> <p>IR: 大于等于 <math>500\text{M}\Omega</math>或 <math>5\Omega\cdot\text{F}</math>(取较小值)</p> <p>No remarkable visual damage</p> <p>Cp change<math>\leq\pm 7.5\%</math> or <math>\pm 0.75\text{pF}</math>, whichever is larger.</p> <p>DF:Not more than 2 times of initial value</p> <p>R*C<math>\geq 500\text{M}\Omega</math> or <math>5\Omega\cdot\text{F}</math>, whichever is smaller</p>	<p>测试温度: <math>40\pm 2^\circ\text{C}</math></p> <p>湿度: 90~95% RH</p> <p>电压: 额定电压</p> <p>测试时间: <math>500\pm 12\text{hrs}</math></p> <p>在室温下放置 <math>24\pm 2</math> (M3L)小时以后测量</p> <p>测量初始电容值。</p> <p>Test temperature: <math>40\pm 2^\circ\text{C}</math></p> <p>Humidity: 90~95% RH</p> <p>Voltage: 100% of the rated voltage</p> <p>Testing time: <math>500\pm 12\text{hrs}</math></p> <p>Measurement to be made after being kept at room temperature for <math>24\pm 2\text{hrs}</math> (M3L)</p> <p>Perform the initial measurement.</p>

备注：该项可靠性试验仅适用于常规产品，不适用于中高压产品。



产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

### 5.16 耐久性 Life Test

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
M3L	外观无明显可见损伤 容量变化在 $\pm 12.5\%$ 以内 DF 为初始值的 2 倍以下 IR: 大于等于 $1000M\Omega$ 或 $5\Omega \cdot F$ (取较小值) No remarkable visual damage Cp change $\leq \pm 12.5\%$ DF: Not more than 2 times of initial value R*C $\geq 1000M\Omega$ or $5\Omega \cdot F$ , whichever is smaller	测试温度：上限类别温度 $\pm 3^{\circ}C$ 电压： 1 倍额定电压 测试时间：1000 小时 在室温下放置 $24 \pm 2$ (M3L) 小时以后测量 Test temperature: Max. Operating Temp. $\pm 3^{\circ}C$ Voltage: 100% of the rated voltag Testing time: 1000 hrs Measurement to be made after being kept at room temperature for $24 \pm 2$ hrs (M3L)

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

## 6. 产品包装 Packing

### 6.1 袋式散装 Bulk Packing

10000 个/袋或按客户要求。Standard packing 10Kpcs/bag; others are according to customer request.

### 6.2 编带式包装 Tape Packing


纸带：4000 个/盘

Paper Tape: Standard taping (8mm paper width), 4Kpcs/reel

塑料带：适合 0603、0805、1206 尺寸规格，厚度大于 0.95mm 的产品，3000 个/盘。

Plastic Tape: Suitable 0603、0805、1206 sizes, for chip thickness over 0.95 mm 3Kpcs/reel are available.

#### 6.2.1 纸带尺寸 Dimensions of Packing Paper




Type	A	B	C	D	T
0603	1.05 ± 0.10	1.85 ± 0.10	4.0 ± 0.10	2.0 ± 0.10	1.1max
0805	1.55 ± 0.15	2.3 ± 0.15	4.0 ± 0.10	2.0 ± 0.10	1.1max
1206	1.95 ± 0.15	3.5 ± 0.15	4.0 ± 0.10	2.0 ± 0.10	1.1max

(单位 unit:毫米 mm)


产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No.
	DRAAW101J/0

### 6.2.2 塑料带尺寸 Dimensions of Embossed Packing




A:  $1.45 \pm 0.20$  B:  $2.25 \pm 0.20$  (0805)      A:  $1.95 \pm 0.20$  B:  $3.50 \pm 0.20$  (1206) (单位 unit:毫米 mm)

### 6.2.3 编带盘尺寸 Dimensions of Reel




### 6.2.4 编带方式 Taping Figure



纸带或塑料带

Paper tape or plastic tape


产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No. DRAAW101J/0
-------------------------------------	--------------------------------



### 6.2.5 编带方法 Taping Method


- ① 包装电容器的编带是顺时针卷绕的，由上往下的方向拉出编带时，传送孔处于编带的右侧。
- ② 在编带的前端，至少留出 5 个间距的引出带。
- ③ 在编带时，必须按下图留出引出带部分或空白部分。
- ④ 在盘带的安装中的产品装错的数量每盘必须小于表示数量的 0.1% 或 1 个为限，不连续发生错误。
- ⑤ 上胶带和下胶带不应超出编带的边缘，不能挡住传送孔。
- ⑥ 传送孔的累计误差为 10 个间距：±0.3 毫米以内。
- ⑦ 上胶带的剥离力矩应在 0.1 至 0.6 牛顿以内，其方向如下图所示。

- ① Tapes for capacitors are wound clockwise. The sprocket holes are to the right as the tape is pulled toward the user.
- ② The top tape and base tape are not attached at the end of the tape for a minimum of 5 pitches.
- ③ Part of the leader and part of the empty tape shall be attached to the end of the tape as follows.
- ④ Missing capacitors number within 0.1% of the number per reel or 1pc, whichever is greater, and are not continuous.
- ⑤ The top tape and bottom tape shall not protrude beyond the edges of the tape and shall not cover sprocket holes.
- ⑥ Cumulative tolerance of sprocket holes, 10 pitches: ±0.3mm.
- ⑦ Peeling off force: 0.1 to 0.6N in the direction shown down.



产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

### 6.2.6 产品标签 Reel Label



标签内容 The Contents of Label、

- (1)  $\frac{TCC}{①}$   $\frac{0805}{②}$   $\frac{M3L}{③}$   $\frac{221}{④}$   $\frac{J}{⑤}$   $\frac{102}{⑥}$   $\frac{B}{⑦}$   $\frac{T}{⑧}$

①陶瓷电容器代号 Code of Ceramic Capacitor、②尺寸 chip size、

③温度特性 dielectrics、④容量 capacitance、⑤容量容差 tolerance、⑥额定电压 rated voltage、

⑦厚度 thickness,⑧ ⑧包装 packing

(2) 产品批号 Lot. No.: C120889A

(3) 数量 Qty: 4000pcs

(4) RoHS:GREEN PARTS 绿色物料

### 6.2.7.外包装 Package

#### 6.2.7.1 包装箱 Carton

##### 6.2.7.1.1 包装箱尺寸 Carton Size

L	W	H
41cm	38.5cm	20.2cm

##### 6.2.7.1.2 数量： 240Kpcs /箱 The Quantity: 240Kpcs /one carton

1 内包装盒=40,000PCS 1 INNER BOX=40,000PCS

1 包装箱 =40,000PCS × 6 包装盒=240,000PCS 1 CARTON=40,000PCS × 6BOX=240,000PCS

RoHS 标识(根据客户要求张贴) according to customer request

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

**6.2.7.2 内包装盒 Inner Box**

**6.2.7.2.1 包装盒尺寸 Size**

L	W	H
18cm	18.5cm	11.8cm

**6.2.7.2.2 数量：40Kpcs /盒**

1 盘=4000PCS      1 REEL=4,000PCS

1 包装盒=4,000PCS × 10 盘 =40,000PCS      1 INNER BOX=4,000PCS × 10REEL =40,000PCS

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

## 7. MLCC 使用注意事项 Precautions on the use of MLCC

### 7.1 电路板设计 PCB Design

#### 7.1.1 电路板图案设计 Design of Land-patterns

下面图和表格给出了部分推荐的设计图案，可以防止安装时焊锡量过多。

同时也给出了不正确的图案。

The following diagrams and tables show some examples recommended patterns to prevent excessive solder amounts (larger fillets which above the component end terminations)

Examples of improper pattern designs are also shown.


电路板设计推荐图案尺寸：

Recommended land dimensions for a typical chip capacitor land patterns for PCBs

波峰焊接时推荐设计的尺寸 (单位: mm):

Recommended land dimensions for wave-soldering (unit: mm)


规格 SIZE		0603	0805	1206
尺寸	L	1.6	2.0	3.2
	W	0.8	1.25	1.6
A		0.8~1.0	1.0~1.4	1.8~2.5
B		0.5~0.8	0.8~1.5	0.8~1.7
C		0.6~0.8	0.9~1.2	1.2~1.6



再流焊接时推荐设计的尺寸 (单位: mm)

Recommended land dimensions for reflow-soldering (unit: mm)

规格 SIZE		0603	0805	1206
尺寸	L	1.6	2.0	3.2
	W	0.8	1.25	1.6
A		0.6~0.8	0.8~1.2	1.8~2.5
B		0.6~0.8	0.8~1.2	1.0~1.5
C		0.6~0.8	0.9~1.6	1.2~2.0









过量的焊锡会影响产品抵抗机械应力的能力，因此在设计图案时应引起注意。

Excess solder can affect the ability of chips to withstand mechanical stresses. Therefore, please take proper precautions when designing land-patterns.

在应用中一些焊接好与坏的情况：

Examples of good and bad solder application

产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0



项目 Item	不推荐结构 Not recommended	推荐结构 Recommended
片状元件和带引线的元件的混合焊接 Mixed mounting of SMD and leaded component		
靠近底座的焊接 Component placement close to the chassis		
在片状元件附近带引线元件的焊接 Hand-soldering of leaded components near mounted components		

### 7.1.2 图案结构

#### Pattern configurations

下面是电容器安装好与坏的样子。选择贴装位置，应尽可能减小电路板在弯曲时受到的机械应力。

The following are examples of good and bad capacitor layout, SMD capacitors should be located to minimize any possible mechanical stresses from board warp or deflection..


	不推荐结构 Not recommended	推荐结构 Recommended
电路板弯曲 Deflection of the board		

对于电路板分拨的电容器，在分拨时受到的机械应力大小与电容器的安装有关。下面推荐了一些好的设计。

To layout the capacitors for the breakaway PC board, it should be noted that the amount of mechanical stresses given depending on capacitor layout. The example below shows recommendations for better design.



产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0







在沿着分拨线分拨电路板时，对产品施加的机械应力与使用的方法关系很大。分折电路板时片状元件受到的疲劳按照如下顺序增大：分折、剪切、V型槽、穿孔。因此，贴装时应该考虑电路板的分拨过程。

When breaking PC boards along their perforations, the amount of mechanical stress on the capacitors can vary according to the method used. The following methods are listed in order from least stressful to most stressful: push-back, slit, -grooving, and perforation. Thus, any ideal SMD capacitor layout must also consider the PCB splitting procedure.

## 7.2 自动贴装注意事项 Considerations for automatic placement

### 贴装机的调整 Adjustment of mounting machine

- ①. 产品在电路板贴装时，不应该受到过大的冲击。
- ②. 必须定期对吸头和定位爪进行检查、维修和更换
- ①. Excessive impact load should not be imposed on the capacitors when mounting the PC boards.
- ②. The maintenance and inspection of the mounters should be conducted periodically.

	不推荐结构 Not recommended	推荐结构 Recommended
单面贴装 Single-sided mounting		
双面贴装 Double-sided mounting		

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0


### 7.3 推荐焊接曲线 Recommended soldering profile

7.3.1 说明：① 产品推荐使用回流焊接工艺；② 大尺寸产品适用于回流焊接工艺

7.3.1 Re: ①flow Soldering is recommended; ②flow soldering is suitable for bigger size MLCCs


### 7.3.2 锡铅焊接曲线 Recommended Sn&Pb soldering profile

#### 再流焊 Reflow soldering




#### 注意 Caution

- ①. 理想状况的焊锡高度为电容器厚度的 1/2 ~1/3，如下图所示：
- ①.The ideal condition is to have solder mass (fillet) controlled to 1/2 to 1/3of the thickness of the capacitor, as shown below:



- ②. 过长的焊接时间会影响端头的可焊性，焊接时间尽可能保持与推荐时间一致。
- ②. Because excessive dwell times can detrimentally affect solderability, soldering duration should be kept as close to recommended times as possible.

#### 波峰焊 Wave solder profile



产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW101J/0

**注意 Caution**

- ①.确保电容器充分预热。
- ②.产品预热和焊接温度差不超过 100~130℃。
- ③.焊接后尽可能慢速冷却。
- ①.Make sure the capacitors are preheated sufficiently.
- ②.The temperature difference between the capacitor and melted solder should not be greater than 100 to 130℃.
- ③.Cooling after soldering should be gradual as possible.

**手工焊接 Hand soldering**

条件:


预热	烙铁头温度	烙铁功率	烙铁头直径	焊接时间	锡膏量	限制条件
$\Delta \leq 130^{\circ}\text{C}$	最高350℃	最大20W	建议1mm	最长5s	$\leq 1/2$ 芯片厚度	请勿使用烙铁头直接接触陶瓷原件

**注意 Caution**

- ①.用尖端最大直径 1.0mm 功率 20W 的焊接烙铁。
- ②.焊接烙铁不要直接接触产品。
- ①.Use a 20w soldering iron with a maximum tip diameter of 1.0mm.
- ②.The soldering iron should not directly touch the capacitor.


**7.3.3 无铅焊接曲线 Recommended Pb-Free soldering profile**

**回流焊接 Reflow soldering**



产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW101J/0

**波峰焊接 Wave solder profile**



#### 7.4 分拨电路板 Handling

Breakaway PC boards (splitting along perforations)

- (1).在电容器或其它贴装后，必须注意因电路板弯曲或变形带来的应力。
- (2).分拨电路板时必须使用专用的夹具，不可以用手拨断。

- (1).When splitting the PC board after mounting capacitors and other components, care is required so as not to give any stresses of deflection or twisting to the board.
- (2).Board separation should not be done manually, but by using the appropriate devices.

#### 7.5 保存 Storage

(1).在下列环境中保存产品：温度 5~40°C；湿度 ≤70% RH

(2).产品自生产之日保存期为一年，产品使用之前请勿拆开编带。

(3).编带拆开后，产品应在三个月内使用。

(4).高介电常数电容器的容值随时间会逐渐减小，所以在电路设计时应充分考虑这一现象。容值减小的电容器在 150°C 热处理 1 小时后容值会恢复到初试值。

(1). Keep the storage environment conditions as following:

Temperature: 5~40°C

Humidity: ≤70% RH

- (2). Don't open the tape until the parts are to be used, and store them within one year since the date printed on the reel.
- (3). Use the chips within 3 months after the tape is opened.
- (4). The capacitance value of high dielectric constant capacitors will gradually decrease with the passage of time, so this should be taken into consideration in the circuit design. If such a capacitance reduction occurs, a heat treatment of 150°C for 1 hour will return the capacitance to its initial level.

#### 7.6 环保申明 Environmental Declaration

- (1).我司所有 MLCC 产品均符合 RoHS 2.0 标准；
  - (2).我司所有 MLCC 产品均符合最新的 REACH 法规要求；
  - (3).我司所有 MLCC 产品均符合 HF 要求。
- (1).All MLCC products of our comply with RoHS 2.0;



**潮州三环（集团）股份有限公司**

**CHAOZHOU THREE-CIRCLE(GROUP)CO.,LTD**

**地址：中国广东省潮州市凤塘三环工业城 邮编（Post Code）：515646**

**ADD:Sanhuan Industrial District,Fengtang Chaozhou,Guangdong,China**

- (2).All MLCC products of our comply with the latest REACH regulations;
- (3).All MLCC products of our comply meet HF requirements.